

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY DOCKET NO. 401612
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 USC 371 AND 37 CFR 1.491		U.S. APPLICATION NO. 107088674
INTERNATIONAL APPLICATION NO. PCT/JP00/06632	INTERNATIONAL FILING DATE September 27, 2000	PRIORITY DATE CLAIMED
TITLE OF INVENTION WIRE ELECTRODE FOR WIRE ELECTRICAL DISCHARGE MACHINE		
APPLICANT(S) FOR DO/EO/US AKIYOSHI, ET AL.		
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:		
1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 USC 371 and 37 CFR 1.491. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 USC 371 and 37 CFR 1.491. 3. <input checked="" type="checkbox"/> This is an express request to begin national examination procedures (35 USC 371(f)). 4. <input checked="" type="checkbox"/> The US has been elected by the expiration of 19 months from the priority date (PCT Article 31). 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 USC 371(c)(2)) a. <input type="checkbox"/> is attached hereto (required only if not communicated by the International Bureau). b. <input checked="" type="checkbox"/> has been communicated by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input type="checkbox"/> An English language translation of the International Application as filed (35 USC 371(c)(2)). 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 USC 371(c)(3)) a. <input type="checkbox"/> are attached hereto (required only if not communicated by the International Bureau). b. <input type="checkbox"/> have been communicated by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input checked="" type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 USC 371(c)(3)). 9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 USC 371(c)(4)). 10. <input type="checkbox"/> An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 USC 371(c)(5)). 11. Nucleotide and/or Amino Acid Sequence Submission a. <input type="checkbox"/> Computer Readable Form (CRF) b. Specification Sequence Listing on: i. <input type="checkbox"/> CD-ROM or CD-R (2 copies); or ii. <input type="checkbox"/> Paper Copy c. <input type="checkbox"/> Statement verifying identity of above copies Items 12 to 19 below concern other document(s) or information included: 12. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98. <input type="checkbox"/> Form PTO-1449 <input type="checkbox"/> Copies of Listed Documents 13. <input checked="" type="checkbox"/> An assignment for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 14. <input checked="" type="checkbox"/> A FIRST preliminary amendment. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 15. <input type="checkbox"/> A substitute specification. 16. <input type="checkbox"/> A change of power of attorney and/or address letter. 17. <input checked="" type="checkbox"/> Application Data Sheet Under 37 CFR 1.76 18. <input checked="" type="checkbox"/> Return Receipt Postcard 19. <input type="checkbox"/> Other items or information:		

U.S. APPLICATION NO. 10/088674		INTERNATIONAL APPLICATION NO. PCT/JP00/06632		ATTORNEY DOCKET NO. 401612	
--	--	---	--	-------------------------------	--

20. <input type="checkbox"/> The following fees are submitted: Basic National Fee (37 CFR 1.492(a)(1)-(5)): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO..... \$1,040.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO..... \$890.00 International preliminary examination fee (37 CFR 1.482) not paid to USPTO, but international search fee (37 CFR 1.445(a)(2)) paid to USPTO..... \$740.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$710.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1) to (4)..... \$100.00				CALCULATIONS PTO USE ONLY	
ENTER APPROPRIATE BASIC FEE AMOUNT=				\$890.00	
Surcharge of \$130.00 for furnishing the National fee or oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date				\$	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	6-20=		x \$ 18.00	\$	
Independent Claims	1- 3 =		x \$ 84.00	\$	
<input type="checkbox"/> Multiple Dependent Claim(s) (if applicable)				+\$280.00 \$	
TOTAL OF ABOVE CALCULATIONS=				\$890.00	
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				\$	
SUBTOTAL=				\$890.00	
Processing fee of \$130.00 for furnishing English Translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date.				\$	
TOTAL NATIONAL FEE=				\$890.00	
Fee for recording the enclosed assignment. The assignment must be accompanied by an appropriate cover sheet. \$40.00 per property				\$40.00	
TOTAL FEE ENCLOSED=				\$930.00	
				Amount to be: refunded \$	
				charged: \$	


a. ☒ A check in the amount of \$930.00 to cover the above fee is enclosed.

b. ☐ Please charge Deposit Account No. 12-1216 in the amount of \$ to cover the above fees. A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 12-1216. A duplicate copy of this sheet is enclosed.


NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:



23548

PATENT TRADEMARK OFFICE



Jeffrey A. Wyand, Reg. No. 29,458
 LEYDIG, VOIT & MAYER, LTD.
 700 Thirteenth Street, N.W., Suite 300
 Washington, DC 20005-3960
 (202) 737-6770 (telephone)
 (202) 737-6776 (facsimile)

Date: March 21, 2002

PATENT
Attorney Docket No. 401612/ASAHINA

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

AKIYOSHI et al.

Application No. Unassigned

Art Unit: Unassigned

Filed: March 21, 2002

Examiner: Unassigned

For: WIRE ELECTRODE FOR WIRE
ELECTRICAL DISCHARGE MACHINE

PRELIMINARY AMENDMENT

Commissioner for Patents
Washington, D.C. 20231

Dear Sir:

Prior to the examination of the above-identified patent application, please enter the following amendments and consider the following remarks.

IN THE SPECIFICATION:

Replace the paragraph beginning at page 1, line 13 with:

In order to increase the machining speed, an example of a wire electrode for a wire electrical discharge machine, wherein core material (i.e., a core) is coated with a layer of Cu-Zn intermetallic compound, is disclosed in HITACHI CABLE REVIEW No. 18 (October 1999). A photograph of a cross section of this wire electrode is shown in Fig. 8. The figure is a magnification of a region near a surface of the wire electrode, wherein the coating layer of Cu-Zn intermetallic compound covering the core can be seen. In Fig. 8, the β phase of the intermetallic compound is seen in a string-like pattern and is surrounded by the α phase. Moreover, the outermost region of the wire electrode consists of only the α phase.

Replace the paragraph beginning at page 1, line 24 with:

The β phase, which has higher Zn concentration than the α phase, has an advantage of increasing machining speed, because the β phase easily evaporates through discharges to blow out object material. On the other hand, the β phase is brittle in a sense of metallography and has a disadvantage that there easily occur cracks during a cold wire drawing process in

In re Appln. of Akiyoshi et al.
Application No. Unassigned

manufacturing a wire electrode. Since the α phase with superior workability surrounds the β phase with difficult workability, a wire electrode as shown in Fig. 8 can be easily formed as a fine wire without any cracks or breaks during a cold wire drawing process.

Replace the paragraph beginning at page 2, line 6 with:

Further, a similar wire electrode for a wire electrical discharge machine is disclosed in Japanese Unexamined Patent Publication No. 300136/1997. Fig. 9 shows concentration of Zn in the radial direction of this wire electrode. The region near the surface of the wire electrode consists of the α phase and the Zn concentration is approximately 30 wt. %. In the case where Zn concentration exceeds 40 wt. %, there appears the β or γ phase having a different crystal structure from that of the α phase. At a depth of 5 to 30 μm from the surface of the wire electrode, the Zn concentration ranges from 35 to 45 wt. % where the α and β phases coexist and the Cu-Zn intermetallic compound with relatively high Zn concentration is formed.

Replace the paragraph beginning at page 3, line 3 with:

The present invention is made to solve the described problems and an object thereof is to increase Zn concentration in the coating layer and to improve the machining speed. A further object of the present invention is to remove object material efficiently and improve the machining speed and accuracy of machining, by improving the rigidity of the wire electrode and suppressing vibration during discharge machining.

Replace the paragraph beginning at page 4, line 4 with:

Fig. 4 is a graph showing a relationship between the thickness of a coating of Cu-Zn alloy in the α phase and machining speed;

Replace the paragraph beginning at page 4, line 7 with:

Fig. 5 is a graph showing a relationship between the thickness of a coating of Cu-Zn intermetallic compound in other than the α phase and machining speed;

In re Appln. of Akiyoshi et al.
Application No. Unassigned

Replace the paragraph beginning at page 4, line 10 with:

Fig. 6 is a graph showing machining speed of a wire electrode for a wire electrical discharge machine according to embodiment 2 of the present invention, compared with that of the conventional wire electrode;

Replace the paragraph beginning at page 4, line 14 with:

Fig. 7 is a graph showing machining speed of a wire electrode for a wire electrical discharge machine according to Embodiments 3 and 4 of the present invention, compared with that of the conventional wire electrode;

Replace the paragraph beginning at page 4, line 18 with:

Fig. 8 is a magnified photograph showing a cross section of the conventional wire electrode for a wire electrical discharge machine; and

Replace the paragraph beginning at page 4, line 20 with:

Fig. 9 is a graph showing Zn concentration in a radial direction of a cross section of a conventional wire electrode for a wire electrical discharge machine.

IN THE CLAIMS:

Replace the indicated claims with:

1. (Amended) A wire electrode for wire electrical discharge machining including a three-layer structure comprising an electrically conductive core, a first coating of Cu-Zn intermetallic compound in other than an α phase surrounding the core, and a second coating of Cu-Zn alloy in the α phase on the first coating, wherein the second coating has a thickness in a range from 5 to 15 μm .

2. (Amended) The wire electrode for wire electrical discharge machining according to Claim 1, wherein the first coating comprises Cu-Zn alloy in a β phase.

3. (Amended) The wire electrode for wire electrical discharge machining according to Claim 1, wherein the core comprises Cu-Zr alloy.

4. (Amended) The wire electrode for wire electrical discharge machining according to Claim 2, wherein the core comprises Cu-Zr alloy.
5. (Amended) The wire electrode for wire electrical discharge machining according to Claim 1, wherein the core comprises Cu-Zn alloy.
6. (Amended) The wire electrode for wire electrical discharge machining according to Claim 2, wherein the core comprises Cu-Zn alloy.

IN THE ABSTRACT:

Replace the Abstract with:

ABSTRACT

A wire electrode for electrical discharge machining has a three-layered structure of an electrically conductive core, a first coating of Cu-Zn intermetallic compound in other than an α phase, and a second coating of Cu-Zn alloy in the α phase on the first coating. The thickness of the second coating is 5 to 15 μm . The first coating layer is preferably Cu-Zn alloy in a β phase. The core is preferably Cu-Zr alloy.

In re Appln. of Akiyoshi et al.
Application No. Unassigned

REMARKS

The foregoing Amendment corrects translational errors and conforms the claims to United States practice. No new matter is added.

Respectfully submitted,

LEYDIG, VOIT & MAYER, LTD.

Jeffrey A. Wyand

Jeffrey A. Wyand
Registration No. 29,458

Suite 300
700 Thirteenth Street, N.W.
Washington, D.C. 20005
Telephone: (202) 737-6770
Facsimile: (202) 737-6776

Facsimile: (202) 737-6776
Date: March 21, 2002
JAW:yes

JC13 Rec'd PCT/PTO 21 MAR 2002

PATENT
Attorney Docket No. 401612/ASAHINA

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

AKIYOSHI et al.

Application No. Unassigned

Art Unit: Unassigned

Filed: March 21, 2002

Examiner: Unassigned

For: WIRE ELECTRODE FOR WIRE
ELECTRICAL DISCHARGE
MACHINEAMENDMENTS TO SPECIFICATION, CLAIMS AND
ABSTRACT MADE VIA PRELIMINARY AMENDMENT*Amendments to the paragraph beginning at page 1, line 13:*

In order to increase the machining speed, an example of a wire electrode for a wire electrical discharge machine, wherein core material (i.e., a core) is coated with a layer of Cu-Zn intermetallic compound, is disclosed in HITACHI CABLE REVIEW No. 18 (October 1999). A photograph of a cross section of this wire electrode is shown in Fig. 8. The figure is a magnification of a region near a surface of the wire electrode, wherein the coating layer of Cu-Zn intermetallic compound covering the core can be seen. In Fig. 8, the β phase of the intermetallic compound is seen in a string-like pattern and is surrounded by the α phase. Moreover, the outermost region of the wire electrode consists of only the α phase.

Amendments to the paragraph beginning at page 1, line 24:

The β phase, which has higher Zn concentration than the α phase, has an advantage ~~to increase of increasing~~ machining speed, because the β phase easily evaporates through discharges to blow out object material. On the other hand, the β phase is brittle in a sense of metallography and has a disadvantage that there easily occur cracks during a cold wire drawing process in manufacturing a wire electrode. Since the α phase with superior workability surrounds the β phase with difficult workability, a wire electrode as shown in Fig. 8 can be easily formed ~~to be~~ as a fine wire without any cracks or breaks during a cold wire drawing process.

In re Appln. of Akiyoshi et al.
Application No. Unassigned

Amendments to the paragraph beginning at page 2, line 6:

Further, a similar wire electrode for a wire electrical discharge machine is disclosed in Japanese Unexamined Patent Publication No. 300136/1997. Fig. 9 shows concentration of Zn in the radial direction of this wire electrode. ~~Region~~ The region near the surface of the wire electrode consists of the α phase and the Zn concentration is approximately 30 wt. %. In the case where Zn concentration exceeds 40 wt. %, there appears the β or γ phase having a different crystal structure from that of the α phase. At ~~the~~ a depth of 5 to 30 μm from the surface of the wire electrode, the Zn concentration ranges from 35 to 45 wt. % where the α and β phases coexist and the Cu-Zn intermetallic compound with relatively high Zn concentration is formed.

Amendments to the paragraph beginning at page 3, line 3:

The present invention is made to solve the ~~above described~~ problems and an object thereof is to increase Zn concentration in the coating layer and to improve the machining speed. A further object of the present invention is to remove object material efficiently and improve the machining speed and accuracy of machining, by improving the rigidity of the wire electrode and suppressing ~~the~~ vibration during discharge machining.

Amendments to the paragraph beginning at page 4, line 4:

Fig. 4 is a graph showing a relationship between the thickness of a coating ~~layer 3~~ of Cu-Zn alloy in the α phase and machining speed;

Amendments to the paragraph beginning at page 4, line 7:

Fig. 5 is a graph showing a relationship between the thickness of a coating ~~layer 2~~ of Cu-Zn intermetallic compound in other than the α phase and machining speed;

Amendments to the paragraph beginning at page 4, line 10:

Fig. 6 is a graph showing machining speed of a wire electrode for a wire electrical discharge machine according to embodiment 2 of the present invention, ~~comparing~~ compared with that of the conventional wire electrode;

Amendments to the paragraph beginning at page 4, line 14:

Fig. 7 is a graph showing machining speed of a wire electrode for a wire electrical discharge machine according to Embodiments 3 and 4 of the present invention, comparing compared with that of the conventional wire electrode;

Amendments to the paragraph beginning at page 4, line 18:

Fig. 8 is a magnified photograph showing a cross section of the conventional wire electrode for a wire electrical discharge machine; and

Amendments to the paragraph beginning at page 4, line 20:

Fig. 9 is a graph showing Zn concentration in a radial direction of a cross section of a conventional wire electrode for a wire electrical discharge machine.

Amendments to existing claims:

1. (Amended) A wire electrode for wire electrical discharge ~~machine~~ machining characterized in that the wire electrode has machining including a ~~three-layered~~ three-layer structure comprising an ~~electroconductive~~ electrically conductive core (1), a first coating layer (2) of Cu-Zn ~~intermetallic~~ intermetallic compound in other than an α phase surrounding the core (1), and a second coating layer (3) of Cu-Zn alloy in the α phase on the exterior of the first coating layer (2), and that the thickness of wherein the second coating layer (3) is has a thickness in a range from 5 to 15 μ m.

2. (Amended) The wire electrode for wire electrical discharge ~~machine~~ machining according to Claim 1, ~~characterized in that~~ wherein the first coating layer (2) comprises Cu-Zn alloy in a β phase.

3. (Amended) The wire electrode for wire electrical discharge ~~machine~~ machining according to Claim 1, ~~characterized in that~~ wherein the core (1) comprises Cu-Zr alloy.

4. (Amended) The wire electrode for wire electrical discharge ~~machine~~ machining according to Claim 2, ~~characterized in that~~ wherein the core (1) comprises Cu-Zr alloy.

5. (Amended) The wire electrode for wire electrical discharge ~~machine~~ machining according to Claim 1, ~~characterized in that~~ wherein the core (1) comprises Cu-Zn alloy.

In re Appln. of Akiyoshi et al.
Application No. Unassigned

6. (Amended) The wire electrode for wire electrical discharge ~~machine~~ machining according to Claim 2, ~~characterized in that~~ wherein the core ~~(1)~~ comprises Cu-Zn alloy.

Amendments to the abstract:

ABSTRACT

~~The present invention aims to increase concentration of Zn in a coating layer to enhance machining speed. Moreover, the present invention aims to perform removal of object material efficiently and enhance machining speed as well as accuracy in machining by increasing rigidity of the wire electrode to suppress vibration thereof during machining process.~~

~~The present invention is characterized in that the~~ A wire electrode for wire electrical discharge ~~machine~~ is constituted as machining has a three-layered structure of an ~~electroconductive~~ electrically conductive core (1), a first coating layer (2) of Cu-Zn ~~intermetallic~~ intermetallic compound in other than an α phase, and a second coating layer (3) of Cu-Zn alloy in the α phase on the exterior of the first coating layer (2), and that the. The thickness of the second coating layer (3) is set to 5 to 15 μm . ~~Furthermore, the~~ The first coating layer (2) is preferably Cu-Zn alloy in a β phase. ~~Moreover, the~~ The core (1) is preferably ~~made of~~ Cu-Zr alloy.

PATENT
Attorney Docket No. 401612/ASAHINA

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

AKIYOSHI et al.

Application No. Unassigned

Art Unit: Unassigned

Filed: March 21, 2002

Examiner: Unassigned

For: WIRE ELECTRODE FOR WIRE
ELECTRICAL DISCHARGE
MACHINE

PENDING CLAIMS AFTER ENTRY OF PRELIMINARY AMENDMENT

1. A wire electrode for wire electrical discharge machining including a three-layer structure comprising an electrically conductive core, a first coating of Cu-Zn intermetallic compound in other than an α phase surrounding the core, and a second coating of Cu-Zn alloy in the α phase on the first coating, wherein the second coating has a thickness in a range from 5 to 15 μm .

2. The wire electrode for wire electrical discharge machining according to Claim 1, wherein the first coating comprises Cu-Zn alloy in a β phase.

3. The wire electrode for wire electrical discharge machining according to Claim 1, wherein the core comprises Cu-Zr alloy.

4. The wire electrode for wire electrical discharge machining according to Claim 2, wherein the core comprises Cu-Zr alloy.

5. The wire electrode for wire electrical discharge machining according to Claim 1, wherein the core comprises Cu-Zn alloy.

6. The wire electrode for wire electrical discharge machining according to Claim 2, wherein the core comprises Cu-Zn alloy.

9/p7s

- 1 -

DESCRIPTION

WIRE ELECTRODE FOR WIRE ELECTRICAL DISCHARGE MACHINE

5

TECHNICAL FIELD

The present invention relates to a wire electrode to be used in a discharge machining with a wire electrical discharge machine.

BACKGROUND ART

10

A wire electrical discharge machine is a device which machines a workpiece by discharges between a wire electrode and the workpiece.

15

In order to increase the machining speed, an example of a wire electrode for a wire electrical discharge machine, wherein core material (i.e. a core) is coated with a layer of Cu-Zn intermetallic compound, is disclosed in HITACHI CABLE REVIEW No.18 (October 1999). A photograph of cross section of this wire electrode is shown in Fig. 8. The figure is a magnification of region near surface of the wire electrode, wherein the coating layer of Cu-Zn intermetallic compound covering the core can be seen. In Fig. 8, β phase of the intermetallic compound is seen in a string-like pattern and is surrounded by α phase. Moreover, the outermost region of the wire electrode consists of only α phase.

20

β phase which has higher Zn concentration than α phase has an advantage to increase machining speed, because β phase easily evaporates through discharges to blow out object material. On the other hand, β phase is brittle in a sense of metallography and has a

25

disadvantage that there easily occur cracks during a cold wire drawing process in manufacturing a wire electrode. Since α phase with superior workability surrounds β phase with difficult workability, a wire electrode as shown in Fig. 8 can be easily formed to be a fine wire without any cracks or breaks during a cold wire drawing process.

Further, a similar wire electrode for a wire electrical discharge machine is disclosed in Japanese Unexamined Patent Publication No.300136/1997. Fig. 9 shows concentration of Zn in radial direction of this wire electrode. Region near surface of the wire electrode consists of α phase and the Zn concentration is approximately 30 wt. %. In the case where Zn concentration exceeds 40 wt. %, there appears β or γ phase having a different crystal structure from that of α phase. At the depth of 5 to 30 μm from the surface of the wire electrode, Zn concentration ranges from 35 to 45 wt. % where α and β phases coexist and Cu-Zn intermetallic compound with relatively high Zn concentration is formed.

As already described, although β and γ phases show the effect to blow out debris of the object material during electrical discharge machining and can enhance the machining speed, those are brittle in a sense of metallography and have a difficulty in cold wire drawing in wire electrode manufacturing.

Thus, in the conventional wire electrode for a wire electrical discharge machine, core material (i.e. a core) is surrounded by a layer of Cu-Zn intermetallic compound comprising β and α phases. Therefore, there are limitations in increasing Zn concentration of the Cu-Zn intermetallic layer and improving machining speed. Further, since β phase is surround by α phase, the effect of improvement in rigidity of the

wire electrode which β phase intrinsically has cannot be exhibited adequately.

The present invention is made to solve the above problems and an object thereof is to increase Zn concentration in the coating layer and to improve the machining speed. A further object of the present invention is to remove object material efficiently and improve the machining speed and accuracy of machining, by improving the rigidity of wire electrode and suppressing the vibration during machining.

10

DISCLOSURE OF INVENTION

The present invention is characterized in that a wire electrode has three-layered structure of an electroconductive core (1), a coating layer (2) made of Cu-Zn intermetallic compounds existing as other than α phase, and an outer coating layer (3) made of Cu-Zn alloy existing as α phase, and that thickness of the coating layer (3) is 5 to 15 μm .

15

Further, the coating layer (2) is preferably Cu-Zn alloy in β phase.

Moreover, the core (1) is preferably made of Cu-Zr alloy.

Furthermore, the core (1) might be made of Cu-Zn alloy.

20

BRIEF DESCRIPTION OF DRAWINGS

Fig. 1 is a diagram showing a cross section of a wire electrode for a wire electrical discharge machine according to the present invention;

25

Fig. 2 is a photograph showing a cross section of a wire electrode for a wire electrical discharge machine according to the present invention;

Fig. 3 is a graph showing Zn concentration in a radial direction of cross section of a wire electrode for a wire electrical discharge machine according to the present invention;

Fig. 4 is a graph showing a relationship between the
5 thickness of a coating layer 3 of Cu-Zn alloy in α phase and machining speed;

Fig. 5 is a graph showing a relationship between the thickness of a coating layer 2 of Cu-Zn intermetallic compound in other than α phase and machining speed;

10 Fig. 6 is a graph showing machining speed of a wire electrode for a wire electrical discharge machine according to embodiment 2 of the present invention, comparing with that of the conventional wire electrode;

Fig. 7 is a graph showing machining speed of a wire electrode
15 for a wire electrical discharge machine according to Embodiments 3 and 4 of the present invention, comparing with that of the conventional wire electrode;

Fig. 8 is a magnified photograph showing cross section of the conventional wire electrode for a wire electrical discharge machine; and

20 Fig. 9 is a graph showing Zn concentration in a radial direction of cross section of a conventional wire electrode for a wire electrical discharge machine.

BEST MODE FOR CARRYING OUT THE INVENTION

25

EMBODIMENT 1

A wire electrode for a wire electrical discharge machine

according to an embodiment of the present invention is described with referring to Fig. 1. Fig. 1 shows a cross section of the wire electrode. The wire electrode according to the present invention has a three-layered structure wherein a coating layer 2 of Cu-Zn intermetallic compound in other than α phase surrounds an electroconductive core 1, and a coating layer 3 of Cu-Zn alloy in α phase is formed outside the coating layer 2. The Cu-Zn intermetallic compound which constitutes the coating layer 2 is in other than α phase and the thickness thereof is increased to the utmost. Since the workability of wire drawing in wire electrode manufacturing becomes worse by increasing the thickness of the phase other than α phase, the thickness of coating layer 3 which is in α phase is increased as much as possible.

Fig. 2 shows a photograph of cross section of the wire electrode of the present invention. There can be clearly seen that the coating layer 3 of Cu-Zn alloy in α phase and the coating layer 2 of Cu-Zn intermetallic compound in other than α phase is clearly separated from each other to form a three-layered structure including the core 1.

The coating layer 2 of Cu-Zn intermetallic compound in other than α phase has higher Zn concentration compared with the coating layer 3 of Cu-Zn alloy in α phase. In Fig. 3, Zn concentration in a radial direction of cross section is shown for the wire electrode of the present invention. In the region where the distance from the wire electrode surface is 0 to 15 μm , the coating layer 3 of Cu-Zn alloy in α phase exists and Zn concentration is around 35 wt. %. In the region where the distance from the wire electrode surface is 15 to 40 μm , the coating layer 2 of Cu-Zn intermetallic layer in other than α phase exists and Zn concentration is around 45 wt. %.

In a machining process with a wire electrical discharge machine, once a single discharge occurs between the workpiece and the wire electrode, the discharge point of the wire electrode is eroded by 5 to 10 μm in a radial direction. Therefore, even if the thickness of the coating layer 3 of Cu-Zn intermetallic compound in α phase is set to 5 to 15 μm according to the present invention, the coating layer 2 of Cu-Zn intermetallic compound in other than α phase and with a high Zn concentration is exposed to the surface by one to three discharge(s) happened at the same point. Cu-Zn inter metallic compound in other than α phase, especially β phase that firstly appears when increasing Zn concentration of α phase, has larger effects of evaporating and blowing off the object material through discharges than those of α phase. Thus, because of appearance of the coating layer 2 of Cu-Zn intermetallic compound in other than α phase at the surface, machining speed by discharges can be enhanced.

Fig. 4 shows a relationship between the thickness of the coating layer 3 of Cu-Zn alloy in α phase and machining speed. The thickness of the coating layer 2 of intermetallic compound in other than α phase is constant to be 25 μm . As is apparent from Fig. 4, machining speed is nearly constant when thickness of the coating layer 3 of Cu-Zn alloy in α phase is not more than 15 μm . That is, when thickness of the coating layer 3 of Cu-Zn alloy in α phase is not more than 15 μm , machining speed can be increased since the coating layer 2 of Cu-Zn intermetallic compound in other than α phase appears at the surface through one or two discharge(s).

When thickness of the coating layer 3 of Cu-Zn alloy in α phase is not more than 5 μm , wire drawing workability in manufacturing

wire electrodes becomes extremely worse. Therefore, thickness of the coating layer 3 of Cu-Zn alloy in α phase is preferably larger than 5 μm and within 15 μm .

Fig. 5 shows a relationship between the thickness of the coating layer 2 of Cu-Zn intermetallic compound in other than α phase and machining speed. The thickness of the coating layer 3 of Cu-Zn alloy in α phase is constant to be 15 μm . The larger the thickness of the coating layer 2 of Cu-Zn intermetallic compound in other than α phase having a high Zn concentration is, the more machining speed is improved.

For a wire electrode having a diameter of 0.3 mm, if the thickness of the coating layer 2 of Cu-Zn intermetallic layer in other than α phase is set to 20 to 40 μm , the coating layer 2 is not exhausted during electric discharge machining process so that machining can be stable and the speed thereof can be remarkably increased.

It is because there occurs difficulty in workability during wire electrode manufacturing that whole cross section except the outermost coating layer 3 cannot be made of Cu-Zn intermetallic compounds in other than α phase.

Although diameter of the wire electrode is 0.3mm in the above example, similar effect can be obtained for the case in which diameter of the wire electrode is 0.1 to 0.4mm. The reason therefore is that diameter of the core 1 is required so as not to break, with bearing tension which is applied for retaining the wire electrode, hence, minimum diameter of the wire electrode including the coating layers 2 and 3 is required to be approximately 0.1mm. Further, maximum diameter is not limited, but considering the process of wire electrode

production and industrial application for the electric discharge machine, approximately 0.4mm is practical. Meanwhile, diameter of the core 1 is about 0.22mm in the case where diameter of the wire electrode is 0.3mm.

5

EMBODIMENT 2

In the present embodiment, a wire electrode has a three-layered structure wherein a core 1 having a diameter of 0.22mm is surrounded by a coating layer 2 of Cu-Zn alloy in β phase having a thickness of 30 μm and further the periphery of the coating layer 2 is coated with a coating layer 3 of Cu-Zn alloy in α phase having a thickness of 10 μm .

In Fig. 6, machining speed of this wire electrode is shown in comparison with that of the conventional wire electrode. As a conventional wire electrode, there was used one wherein a core having a diameter of 0.22mm is surrounded by Cu-Zn intermetallic layer having a thickness of 20 μm and in which β phase is surrounded by α phase, and the periphery of the intermetallic layer is surrounded by Cu-Zn alloy in α phase having a thickness of not more than 5 μm . As core material, Cu-Zn alloy with 35 wt. % Zn concentration was used for both of the present embodiment and the conventional wire electrode.

In Fig. 6, discharge energy IP is shown in abscissa while machining speed is shown in ordinate, and a curved line S1 denotes the wire electrode in the present embodiment while a curved line P1 denotes the conventional wire electrode. For the wire electrode of the present embodiment, an increase in machining speed by 30 mm^2/min is seen at maximum compared with the conventional wire, which is found to be

25

very useful in industrial application.

EMBODIMENT 3

A wire electrode is exposed to extremely high temperature
5 during wire electrical discharge machining. In the present embodiment,
therefore, Cu-Zr alloy which shows little degradation in electrical
conductivity and in mechanical strength to suppress vibration of the
wire electrode even at a high temperature is used for a core 1, a coating
layer 2 of Cu-Zn intermetallic compound in other than α phase is formed
10 on the periphery of the core 1, and further a coating layer 3 of Cu-Zn
alloy in α phase is formed on the periphery of the coating layer 2 to form
a wire electrode having a three-layered structure.

In Fig. 7, machining speed of this wire electrode is shown in
comparison with that of the conventional wire electrode. As the
15 conventional wire electrode, there was used one wherein a core of Cu-Zn
alloy having a diameter of 0.22mm is surrounded by Cu-Zn intermetallic
layer having a thickness of 20 μm and in which β phase is surrounded
by α phase, and the periphery of the intermetallic layer is surrounded by
Cu-Zn alloy in α phase having a thickness of not more than 5 μm is
20 used.

In Fig. 7, discharge energy IP is shown in abscissa while
machining speed is shown in ordinate, and a curved line S2 denotes the
wire electrode of the present embodiment while a curved line P2 denotes
the conventional wire. The wire electrode of the present embodiment,
25 in addition to an effect of blowing off the debris originated from
discharges thanks to the coating layer 2 of Cu-Zn intermetallic
compound in other than α phase, decreases an energy loss thanks to

improvement in electrical conductivity, resulting in increase of energy contributing for discharges and increase in machining speed by 30 mm²/min at maximum compared with the conventional wire electrode, which is found to be very useful in industrial application.

5 Further, similar effect of increase in machining speed thanks to the coating layers 2 and 3 can be obtained when the core 1 of Cu-Zr alloy is substituted by inexpensive and easily available Cu-Zn alloy which has higher tensile strength so as to suppress vibration of the wire electrode.

10

EMBODIMENT 4

In the present embodiment, a wire electrode has a three-layered structure, wherein a coating layer 2 of Cu-Zn alloy in β phase is formed to surround a core 1 of Cu-Zr alloy and the periphery of the coating layer 2 is coated with a coating layer 3 of Cu-Zn alloy in α phase.

15 In Fig. 7, machining speed of the wire electrode according to the present embodiment is shown with a curved line S3. In addition to an effect of β phase Cu-Zn intermetallic compound layer 2 to blow off the debris generated through discharges, decrease in energy loss thanks to improvement in electrical conductivity results in increase of energy contributing for discharges so that machining speed is increased like in the case of Embodiment 3, thereby the wire electrode of the present embodiment is very useful in an industrial application.

25 Further, similar effect of increase in machining speed thanks to the coating layers 2 and 3 can be obtained when the core 1 of Cu-Zr alloy is substituted by inexpensive and easily available Cu-Zn alloy which has higher tensile strength so as to suppress vibration of the wire

electrode.

INDUSTRIAL APPLICABILITY

According to Embodiment 1 of the present invention, since
5 the thickness of the coating layer 3 of Cu-Zn alloy in α phase is set to 5 to
15 μm , the wire electrode of fine diameter is easily formed without
generation of any cracks and breaks even if the thickness of the coating
layer 2 of Cu-Zn metallic compound in other than α phase is increased,
and also high machining speed can be obtained thanks to the existence
10 of the coating layer 2 of Cu-Zn metallic compound in other than α phase
with high Zn concentration.

According to Embodiment 2 of the present invention, since
the thickness of the coating layer 3 of Cu-Zn alloy in α phase is set to 5 to
15 μm , the wire electrode of fine diameter can be easily formed without
generation of any cracks and breaks even if the thickness of the coating
layer 2 of Cu-Zn alloy in β phase is increased. Further, high machining
speed can be obtained thanks to the existence of the coating layer 2 of
Cu-Zn alloy in β phase with high Zn concentration which has a large
effect of blowing off the object material during discharges. Furthermore,
20 since rigidity of the wire electrode is increased by the existence of β
phase, vibration of the wire electrode during machining process is
suppressed so that elimination of the object material is efficiently
performed, and machining speed as well as accuracy in machining are
enhanced.

25 According to Embodiment 3 of the present invention, since
the thickness of the coating layer 3 of Cu-Zn alloy in α phase is set to 5 to
15 μm , the wire electrode of fine diameter is easily formed without

generation of any cracks and breaks even if the thickness of the coating layer 2 of Cu-Zn metallic compound in other than α phase is increased, and also high machining speed can be obtained thanks to the existence of the coating layer 2 of Cu-Zn metallic compound in other than α phase with high Zn concentration. Furthermore, by using Cu-Zr alloy for the core, electrical conductivity does not decrease even at a high temperature, which results in suppressing the discharge energy loss at the wire electrode and can increase the machining speed.

Meanwhile, by using Cu-Zn alloy with a high tensile strength for the core 1, vibration of the wire electrode is suppressed and higher machining speed can be achieved.

According to Embodiment 4 of the present invention, since the thickness of the coating layer 3 of Cu-Zn alloy in α phase is set to 5 to 15 μm , the wire electrode of fine diameter can be easily formed without generation of any cracks and breaks even if the thickness of the coating layer 2 of Cu-Zn alloy in β phase is increased. Furthermore, high machining speed can be obtained thanks to the existence of the coating layer 2 of Cu-Zn alloy in β phase with high Zn concentration which has a large effect of blowing off the object material during discharges. Further, since rigidity of the wire electrode is increased by the existence of β phase, vibration of the wire electrode during machining process is suppressed so that elimination of the object material is efficiently performed, and machining speed as well as accuracy in machining are enhanced. Furthermore, by using Cu-Zr alloy for the core, electrical conductivity does not decrease even at a high temperature, which results in suppressing the discharge energy loss at the wire electrode and can increase the machining speed.

Meanwhile, by using Cu-Zn alloy with a high tensile strength for the core 1, vibration of the wire electrode is suppressed and higher machining speed can be achieved.

CLAIMS

1. A wire electrode for wire electrical discharge machine characterized in that the wire electrode has a three-layered structure comprising an electroconductive core (1), a coating layer (2) of Cu-Zn intermetallic compound in other than α phase surrounding the core (1), and a coating layer (3) of Cu-Zn alloy in α phase on the exterior of the coating layer (2), and that the thickness of the coating layer (3) is 5 to 15 μm .

10

2. The wire electrode for wire electrical discharge machine according to Claim 1, characterized in that the coating layer (2) comprises Cu-Zn alloy in β phase.

15

3. The wire electrode for wire electrical discharge machine according to Claim 1, characterized in that the core (1) comprises Cu-Zr alloy.

4. The wire electrode for wire electrical discharge machine according to Claim 2, characterized in that the core (1) comprises Cu-Zr alloy.

20

5. The wire electrode for wire electrical discharge machine according to Claim 1, characterized in that the core (1) comprises Cu-Zn alloy.

25

6. The wire electrode for wire electrical discharge machine

according to Claim 2, characterized in that the core (1) comprises Cu-Zn alloy.

ABSTRACT

The present invention aims to increase concentration of Zn in a coating layer to enhance machining speed. Moreover, the present invention aims to perform removal of object material efficiently and enhance machining speed as well as accuracy in machining by increasing rigidity of the wire electrode to suppress vibration thereof during machining process.

The present invention is characterized in that the wire electrode for wire electrical discharge machine is constituted as a three-layered structure of an electroconductive core (1), a coating layer (2) of Cu-Zn intermetallic compound in other than α phase and a coating layer (3) of Cu-Zn alloy in α phase on the exterior of the coating layer (2), and that the thickness of the coating layer (3) is set to 5 to 15 μm . Furthermore, the coating layer (2) is preferably Cu-Zn alloy in β phase. Moreover, the core (1) is preferably made of Cu-Zr alloy.

FIG. 1




FIG. 2




FIG. 3




FIG. 4





FIG. 5



THICKNESS OF Cu-Zn ALLOY LAYER 2
OTHER THAN α PHASE (μm)

FIG. 6




FIG. 7





FIG. 8







FIG. 9



Declaration and Power of Attorney for Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

私は、以下に記名された発明者として、ここに下記の通り宣言する：

As a below named inventor, I hereby declare that:

私の住所、郵便の宛先そして国籍は、私の氏名の後に記載された通りである。

My residence, post office address and citizenship are as stated next to my name

下記の名称の発明について、特許請求範囲に記載され、且つ特許が求められている発明主題に関して、私は、最初、最先且つ唯一の発明者である（唯一の氏名が記載されている場合）か、或いは最初、最先且つ共同発明者である（複数の氏名が記載されている場合）と信じている。

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

WIRE ELECTRODE FOR WIRE ELECTRICAL

DISCHARGE MACHINE

上記発明の明細書はここに添付されているが、下記の欄がチェックされている場合は、この限りでない：

the specification of which is attached hereto unless the following box is checked:

☐ _____ の日に出席され、
この出願の米国出願番号または PCT 国際出願番号は、
_____ であり、且つ
_____ の日に補正された出願（該当する場合）

☒ was filed on September 27, 2000
as United States Application Number or
PCT International Application Number
PCT/JP00/06632 and was amended on
_____ (if applicable).

私は、上記の補正書によって補正された、特許請求範囲を含む上記明細書を検討し、且つ内容を理解していることをここに表明する。

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

私は、連邦規則法典第 37 編規則 1.56 に定義されている、特許性について重要な情報を開示する義務があることを認める。

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56

Japanese Language Declaration (日本語宣言書)

私は、ここに、以下に記載した外国での特許出願または発明者証の出願、或いは米国以外の少なくとも一国を指定している米国法典第35編第365条(a)によるPCT国際出願について、同第119条(a)-(d)項又は第365条(b)項に基づいて優先権を主張するとともに、優先権を主張する本出願の出願日より前の出願日を有する外国での特許出願または発明者証の出願、或いはPCT国際出願については、いかなる出願も、下記の枠内をチェックすることにより示した。

I hereby claim foreign priority under Title 35, United States Code, Section 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT International application which designated at least one country other than the United States listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application for which priority is claimed.

Prior Foreign Application(s)
外国での先行出願

Priority Not Claimed
優先権主張なし

(Number) (番号)	(Country) (国名)	(Day/Month/Year Filed) (出願日/月/年)	<input type="checkbox"/>
(Number) (番号)	(Country) (国名)	(Day/Month/Year Filed) (出願日/月/年)	<input type="checkbox"/>

私は、ここに、下記のいかなる米国仮特許出願についても、その米国法典第35編第119条(e)項の利益を主張する。

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.

(Application No.) (出願番号)	(Filing Date) (出願日)	(Application No.) (出願番号)	(Filing Date) (出願日)
-----------------------------	------------------------	-----------------------------	------------------------

私は、ここに、下記のいかなる米国出願についても、その米国法典第35編第120条に基づく利益を主張し、又米国を指定するいかなるPCT国際出願についても、その同第365条(c)に基づく利益を主張する。また、本出願の各特許請求の範囲の主題が、米国法典第35編第112条第1段に規定された態様で、先行する米国出願又はPCT国際出願に開示されていない場合においては、その先行出願の出願日と本国内出願日またはPCT国際出願日との間の期間中に入手された情報で、連邦規則法典第37編規則1.56に定義された特許性に関わる重要な情報について開示義務があることを承認する。

I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s), or 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of application.

(Application No.) (出願番号)	(Filing Date) (出願日)	(Status: Patented, Pending, Abandoned) (現況: 特許許可、係属中、放棄)
(Application No.) (出願番号)	(Filing Date) (出願日)	(Status: Patented, Pending, Abandoned) (現況: 特許許可、係属中、放棄)

私は、ここに表明された私自身の知識に係わる陳述が真実であり、且つ情報と信ずることに基づく陳述が、真実であると信じられることを宣言し、さらに、故意に虚偽の陳述などを行った場合は、米国法典第18編第1001条に基づき、罰金または拘禁、若しくはその両方により処罰され、またそのような故意による虚偽の陳述は、本出願またはそれに対して発行されるいかなる特許も、その有効性に問題が生ずることを理解した上で陳述が行われたことを、ここに宣言する。

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Japanese Language Declaration
(日本語宣言書)

委任状： 私は本出願を審査する手続を行い、且つ米国特許商標庁との全ての業務を遂行するために、記名された発明者として、下記の弁護士及び／または弁理士を任命する。(氏名及び登録番号を記載すること)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith (list name and registration number).

書類送付先

**23548**

PATENT TRADEMARK OFFICE

Send Correspondence to:

直通電話連絡先：(氏名及び電話番号)

**23548**

PATENT TRADEMARK OFFICE

Direct Telephone Calls to: (name and telephone number)


唯一または第一発明者氏名		1-00	Full name of sole or first inventor	
		Masao AKIYOSHI		
発明者の署名	日付	Inventor's signature	Date	
		Masao Akiyoshi	21/2/2002	
住所		Residence	JPX	
		Chiyoda-ku, Tokyo 100-8310 Japan		
国籍		Citizenship		
		Japanese		
郵便の宛先		Post Office Address		
		c/o MITSUBISHI DENKI KABUSHIKI KAISHA, 2-3, Marunouchi 2-chome, Chiyoda-ku, Tokyo 100-8310 Japan		
第二共同発明者がいる場合、その氏名		2-00	Full name of second joint inventor, if any	
		Seiji SATOU	21/2/2002	
第二共同発明者の署名	日付	Second inventor's signature	Date	
		Seiji Satou		
住所		Residence	JPX	
		Chiyoda-ku, Tokyo 100-8310 Japan		
国籍		Citizenship		
		Japanese		
郵便の宛先		Post Office Address		
		c/o MITSUBISHI DENKI KABUSHIKI KAISHA, 2-3, Marunouchi 2-chome, Chiyoda-ku, Tokyo 100-8310 Japan		

(第三以下の共同発明者についても同様に記載し、署名をすること)

(Supply similar information and signature for third and subsequent joint inventors.)

第3の共同発明者の氏名 (該当する場合)	3-00	Full name of third joint inventor, if any	Seigi AOYAMA
同第3発明者の署名	日付	Third Inventor's signature	Seigi Aoyama 18/2/2002
住所		Residence	Kitaibaraki-shi, Ibaraki 319-1537 Japan JPX
国籍		Citizenship	Japanese
郵便の宛先		Post Office Address	144, Shimosoda, Hanakawa-cho,
			Kitaibaraki-shi, Ibaraki 319-1537 Japan
第4の共同発明者の氏名 (該当する場合)	4-00	Full name of forth joint inventor, if any	Hiromitsu KURODA
同第4発明者の署名	日付	Forth Inventor's signature	Hiromitsu Kuroda 18/2/2002
住所		Residence	Hitachi-shi, Ibaraki 319-1416 Japan JPX
国籍		Citizenship	Japanese
郵便の宛先		Post Office Address	2-27-31, Tajiri-cho, Hitachi-shi,
			Ibaraki 319-1416 Japan
第5の共同発明者の氏名 (該当する場合)	5-00	Full name of fifth joint inventor, if any	Takamitsu KIMURA
同第5発明者の署名	日付	Fifth Inventor's signature	Takamitsu Kimura 18/2/2002
住所		Residence	Hitachi-shi, Ibaraki 319-1416 Japan JPX
国籍		Citizenship	Japanese
郵便の宛先		Post Office Address	7-36-27-203, Kawajiri-cho, Hitachi-shi,
			Ibaraki 319-1416 Japan

United States Patent & Trademark Office
Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☒ *Scanned copy is best available. Figures are dark.*